

INSULBOOT® Polyolefin Heat Shrink Tubing

DON'T TAPE IT, INSULBOOT IT!™

Kv Rating (Material)	InsulBoot P/N	Size (mm)	linear inches before shrink	diameter before shrink (inches)	diameter after shrink (inches)	diameter before shrink (mm)	diameter after shrink (mm)	normal wall thickness before shrink (mm)	min. wall thickness after shrink (mm)	feet per roll / feet per box	weight per box (Kg, Lbs)	Raychem P/N	3M P/N	CANUSA P/N
S1-10 4-24 Kv. (red Polyolefin)	HSMV-0001	25/10	3.09	0.98	0.39	25	10	1.10 ± 0.1	2.40 ± 0.1	65/390	14, 30.8	BPTM30/12	BBI-3A 3M	CBTM-0190 19/5.5
	HSMV-0002	30/12	3.71	1.18	0.47	30	12	1.10 ± 0.1	2.40 ± 0.1	65/390	22, 48.4	BPTM30/12	BBI-3A 3M	CBTM-0330 33/10.1
	HSMV-0003	40/16	4.95	1.57	0.59	40	15	1.10 ± 0.1	2.40 ± 0.1	65/325	22, 48.4	BPTM50/20	BBI-3A 3M	CBTM-0520 52/19
	HSMV-0004	50/20	6.18	1.97	0.79	50	20	1.10 ± 0.1	2.50 ± 0.1	65/262	23, 50.6	BPTM50/20	BBI-3A 3M	CBTM-0520 52/19
	HSMV-0005	65/25	8.04	2.56	1.02	65	26	1.10 ± 0.1	2.50 ± 0.1	65/195	23, 50.6	BPTM75/30	BBI-4A 3M	CBTM-0698 69.8/25.4
	HSMV-0006	75/30	9.28	2.95	1.18	75	30	1.10 ± 0.1	2.60 ± 0.1	82/246	23, 50.6	BPTM75/30	BBI-4A 3M	CBTM-0698 69.8/25.4
	HSMV-0007	80/32	9.89	3.15	1.26	80	32	1.10 ± 0.1	2.60 ± 0.1	65/135	18, 39.6	BPTM80/32	BBI-5A 3M	CBTM-0889 88.9/29.9
	HSMV-0008	100/40	12.37	3.94	1.57	100	40	1.10 ± 0.1	2.70 ± 0.1	65/135	20, 44	BPTM100/40	BBI-6A 3M	CBTM-119.3/39.9
	HSMV-0009	120/50	14.84	4.72	1.97	120	50	1.10 ± 0.1	2.70 ± 0.1	65/135	25, 55	BPTM120/50	BBI-7A 3M	CBTM-119.3/39.9
	HSMV-0010	150/60	18.55	5.91	2.36	150	60	1.10 ± 0.1	2.70 ± 0.1	65/65	20, 44	BPTM150/60	BBI-8A 3M	CBTM-1701 170.1/58.4
	HSMV-0011	175/75	22.26	7.09	2.76	180	70	1.10 ± 0.1	3.0 ± 0.01	82/82	24, 52.8	BPTM175/70	BBI-9A 3M	CBTM-1701 170.1/58.4
	HSMV-0012	210/84	25.97	8.27	3.31	210	84	1.10 ± 0.1	3.0 ± 0.01	82/82	37, 80	BPTM205/110	BBI-10A 3M	-
	HSMV-0013	230/92	28.45	9.06	3.62	230	92	1.10 ± 0.1	3.0 ± 0.01	82/82	38, 83	-	BBI-10A 3M	-
S1-35 25-35 Kv. (red Polyolefin)	HSHV-0001	25/10	3.09	0.98	0.39	25	10	1.80 ± 0.2	3.50 ± 0.1	49/344	28, 61.6	BBIT25/10	BBI-3A 3M	CBTH-0279 27.9/8.9
	HSHV-0002	30/12	3.71	1.18	0.47	30	12	1.80 ± 0.2	3.50 ± 0.1	49/295	33, 72.6	BBIT30/12	BBI-3A 3M	CBTH-0279 27.9/8.9
	HSHV-0003	40/16	4.95	1.57	0.63	40	16	1.80 ± 0.2	3.50 ± 0.1	49/196	21, 46.2	BBIT40/16	BBI-3A 3M	CBTH-0508 50.8/16
	HSHV-0004	50/20	6.18	1.97	0.79	50	20	1.80 ± 0.2	4.0 ± 0.1	49/196	28, 61.6	BBIT50/20	BBI-3A 3M	CBTH-0508 50.8/16
	HSHV-0005	60/24	7.42	2.36	0.94	60	24	1.80 ± 0.2	4.0 ± 0.1	49/147	23, 50.6	BBIT65/25	BBI-4A 3M	CBTH-0680 68/22.1
	HSHV-0006	65/25	8.04	2.56	0.98	65	25	1.80 ± 0.2	4.0 ± 0.1	49/147	25, 55	BBIT65/25	BBI-4A 3M	CBTH-0680 68/22.1
	HSHV-0007	70/28	8.66	2.76	1.10	70	28	1.80 ± 0.2	4.0 ± 0.1	49/147	28, 61.6	BBIT75/30	BBI-5A 3M	CBTH-0899 89.9/29.9
	HSHV-0008	75/30	9.28	2.95	1.18	75	30	2.0 ± 0.2	4.0 ± 0.1	49/147	29, 63.8	BBIT75/30	BBI-5A 3M	CBTH-0899 89.9/29.9
	HSHV-0009	80/32	9.89	3.15	1.26	80	32	2.0 ± 0.2	4.0 ± 0.1	49/147	33, 72.6	BBIT75/30	BBI-5A 3M	CBTH-0899 89.9/29.9
	HSHV-0010	100/40	12.37	3.94	1.57	100	40	2.0 ± 0.2	4.50 ± 0.1	49/98	27, 59.4	BBIT100/40	BBI-7A 3M	CBTH-1199 119.9/39.9
	HSHV-0011	120/50	14.84	4.72	1.97	120	50	2.0 ± 0.2	4.50 ± 0.1	49/98	35, 77	BBIT120/50	BBI-8A 3M	CBTH-1199 119.9/39.9
	HSHV-0012	150/60	18.55	5.91	2.36	150	60	2.0 ± 0.2	4.50 ± 0.1	49/49	21, 46.2	BBIT150/60	BBI-9A 3M	CBTH-1702 167.6/65
	HSHV-0013	175/75	21.64	6.89	3.15	175	80	2.0 ± 0.2	4.50 ± 0.1	49/49	23, 50.6	BBIT175/80	BBI-9A 3M	CBTH-1702 167.6/65
Heat shrink tape	HST1-2-R	2"	-	-	-	-	-	-	-	16/160	-	HVBT-2-R	-	-